




FOAMGLAS® T4+ CELLULAR GLASS



RIGID FOAM INSULATION

Owens Corning® FOAMGLAS® T4+ cellular glass insulation is a closed-cell, high-performance, rigid foam board specifically designed for building and roofing applications. It provides a unique combination of properties that offer an alternative to other types of building insulation. FOAMGLAS® T4+ insulation is designed for use where mechanical attachment is required.

Features



High Compressive Strength



Non-Combustible¹



Waterproof²



Vapor Impermeable



Dimensionally Stable



Insect and Pest Resistant



Chemically Resistant



Zero Deflection

¹ Unfaced only

² Per ASTM D5385/C1306

Standards, Code Compliance

- UL (Underwriters Laboratories) Roof Deck Constructions, tested in accordance with UL 1256
- FM (Factory Mutual) Class 1 Roof Decks
- ASTM E119 Fire-Resistance-Rated Roof Assemblies
- UL and FM Wind-Uplift-Rated Assemblies
- T4+ cellular glass material meets or exceeds all physical & thermal property requirements of ASTM C1902 Type II

Physical Properties³

PROPERTY	TEST METHOD	VALUE
Composition	–	Inorganic; soda lime glass
Density, minimum pcf (kg/m ³)	ASTM C303	5.5 (88)
Service Temperature, °F (°C)	–	-445 to 806 (-265 to 430)
Water Absorption, maximum vol %	ASTM C240	0.1%
Water Vapor Permeability, maximum perm-in (ng/Pa-s-m)	ASTM E96	0.005 (.007)
Mold/Mildew Resistance	ASTM C1338	Pass
Corrosion Resistance	ASTM C1617	Pass (steel, less than DI water)
Hydrostatic Resistance, minimum equivalent water height in feet (meters)	ASTM D5385/C1306	34.5 (10.5)
Coefficient of Linear Thermal Expansion, maximum in/in/°F (mm/mm/°C)	ASTM E228	5.0 x 10 ⁻⁶ (9.0 x 10 ⁻⁶)
Dimensional Stability ⁴ %, maximum		
@ 158°F/97% R.H.	ASTM D2126	1.0%
@ -40°F/ambient R.H.		1.0%
@ 200°F/ambient R.H.		1.0%
Compressive Strength (capped), minimum psi (kPa)	ASTM C165 Procedure A/ ASTM C240	87 (600)
Flexural Strength, psi (kPa), minimum	ASTM C203	65.3 (450)
Modulus of Elasticity, ksi (MPa), Approximate (ν = 0.25)		
Perpendicular	ASTM C623	145 (1,000)
Parallel		164 (1,131)
Combustibility ¹	ASTM E136	Non-combustible
Surface Burning Characteristics ^{1,5} , maximum		
Flame Spread Index	ASTM E84	0
Smoke Developed Index		0
Thermal Resistance ⁶ per inch @ 75°F (24°C) mean temperature ³ , Hr-ft ² -°F/BTU (m ² -°C/W)	ASTM C518/ASTM C177	3.4 (0.59)

³ Properties shown are representative values for 1-inch-thick material unless otherwise specified. Cellular glass may exhibit different physical properties based upon thickness. Certain physical properties are listed by minimum and maximum values per ASTM C1902. For details on specific test methods, please contact Owens Corning at 1-800-GET-PINK.

⁴ Maximum change in any dimension.

⁵ These laboratory tests are not intended to describe the hazards under actual fire conditions. Verify compliance with all required applicable fire assemblies.

⁶ R means the resistance to heat flow; the higher the value, the greater the insulation power. This insulation must be installed properly to get the market R-value. Follow the manufacturer's instructions carefully. The U.S. FTC requires the R-value of home insulation to be measured at 75°F mean temperature. R-value claims should always be compared at the same mean temperature. Because rigid foam plastic insulation products are not all aged in accordance with the same standards, it is useful to publish comparison R-value data.

Technical Information

FOAMGLAS® cellular glass insulation is an insulating material to be installed beneath a protective roof membrane in roof applications designed to meet required construction and service-loading conditions as determined by a licensed engineer or architect of record. [See Owens Corning FOAMGLAS® Commercial Roofing Design Guide](#)

Availability⁷

PRODUCT	R-VALUE	THICKNESS	WIDTH	LENGTH	COUNTRY OF ORIGIN
Unfaced Block	5.0–23.8	1.5"–7" in 0.5" increments	18"	24"	USA

7 Tapered products are available in 1/8 inch, 1/4 inch, and 1/2 inch per foot slope. Please contact Owens Corning at 1-800-GET-TECH.

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation, and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets, and enhancing lives. More information can be found at www.owenscorning.com.

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for, the accuracy or reliability of data associated with particular uses of any product described herein.

Notes

For additional information on FOAMGLAS® T4+ insulation or systems, please contact Owens Corning at any of our worldwide offices or visit us at owenscorning.com/foamglas.

The information contained herein is accurate and reliable to the best of our knowledge. But, because Pittsburgh Corning, LLC has no control over installation workmanship, accessory materials, or conditions of application, NO EXPRESSED OR IMPLIED WARRANTY OF ANY KIND, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE as to the performance of an installation containing Owens Corning products. In no event shall Pittsburgh Corning, LLC be liable for any damages arising because of product failure, whether incidental, special, consequential, or punitive, regardless of the theory of liability upon which any such damages are claimed. Pittsburgh Corning, LLC provides written warranties for many of its products, and such warranties take precedence over the statements contained herein.



PITTSBURGH CORNING, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OH 43659 USA

1-800-GET-PINK®
www.owenscorning.com/foamglas